



Technical Data Sheet

KBR-01

Technical Name: Solution butadiene Rubber

CAS #: 9003-17-2

Appearance: Amber Bales

Technical Parameters:

	Min	Max
Volatile Matter		0.50%
CIS Content	94.0%	
Ash		0.20%
Raw Mooney Viscosity	40.0	50.0
Compound Mooney Viscosity	52.0	66.0
Tensile Strength 35 min	165.0	240.0
Elongation 35 min	410%	590%
300% Modulus 25 min	80.0	120.0
300% Modulus 35 min	85.0	120.0
300% Modulus 50 min	85.0	120.0
Gel Content		2.00

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.

1665 Enterprise Parkway, Twinsburg, OH, 44087 Tel: (330) 920-8023 Fax: (330) 920-0971