



Technical Data Sheet

TBEP

Technical Name: Tributoxylethyl Phosphate
CAS #: 78-51-3 95-98%/111-76-2 3.0%
Appearance: Slightly yellow, oily liquid

Technical Parameters:

	Min	Max
Specific Gravity	1.007	1.033
Acid Number		0.6
Moisture		0.2%
Color Gardner APHA	0	75

Other information not reported on the COA;

Refractive Index @ 25 C 1.4340+- 0.0040

Viscosity @ 25 C approx 12 cPs

Applications: TBEP is used as a low temperature, low modulus plasticizer for polar and semi-polar elastomers such as CR, NBR, SBR/NBR, NBR/PVC. It is also an effective leveling agent for acrylic resin-based polishes

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.

1665 Enterprise Parkway, Twinsburg, OH, 44087 Tel: (330) 920-8023 Fax: (330) 920-0971