



Technical Data Sheet

POLYCOAT RLS-40

Technical Name: Anti-Tack Dip for Elastomeric Compounds
CAS #: Mixture
Appearance: Liquid / White

Technical Parameters:

	Min	Max
PH	7.50	8.30
Solids	31.50%	38.50%

Typical Properties not reported on the COA;

Specific Gravity 1.022

Density #s/gal 7.55

Stability of concentrate will not settle

RLS40 imparts a thin film, seimi-transparent, coating that dries quickly and bonds well to the rubber surface

Special Handling Instructions: Keep from freezing must be agitated once diluted.

RLS-40 is environmentally friendly and contains no zinc, alpha quartz or SARA reportable compounds

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.

1665 ENTERPRISE PARKWAY, TWINSBURG, OH, 44087 Tel: (330) 920-8023 Fax: (330) 920-0971